

MKR 3000 Polyethylene Wax Prills

PRODUCT SPECIFICATION OF 197

Description: MKR 3000 Polyethylene Wax Prills

Issue: 1

Drop Melting Point	D.127	112 – 118°C
Congeaing Point	D.938	101 – 107°C
Needle Penetration at 25°C dmm	D.1321	1.9 – 2.1
Needle Penetration at 54°C dmm	D.1321	18.0 – 20.0
Viscosity at 149 °C	D.3236	20 – 40
Colour (visual)		White
Form		Spray cooled prills

NB This document nullifies and replaces all previous documents referring to this product.